

# Two-Part room temperature curing adhesive

## LYT-CP30

LYT-CP30 is a two-part silicon-based liquid thermal conductive gap filler with a thermal conductivity of 3.0W/m-K. The product has good thixotropy and low viscosity after mixing in a 1:1 ratio, making it easy to dispense or print. When subjected to external force, it can be easily filled into the surface of the heating device and the surrounding gaps, forming a thermal conductive film bridge with the heat sink.

After curing at room temperature or accelerated curing at high temperature, the product has a good elastic modulus, which helps to alleviate the stress released by the thermal expansion of the heating device after heating and protects the components from damaged.



### FEATURES AND BENEFITS

- Thermal conductivity :3.0 W/m -K
- Cure at room temperature or accelerated at high temperatures
- Excellent interfacial wettability
- Low viscosity for easy dispensing or printing application
- Low BLT and low thermal resistance
- No residual stress after curing, which effectively protects the precision electronic components from damage

### APPLICATION

- Electric vehicle power battery module
- Automotive Electronics
- LED lighting
- Mainframe and small office network equipment
- Large storage data center
- Smartphone Modules and Consumer Electronics

Long Young Electronic Co.

Tel: 86.512.57668990

Fax: 86.512.57669500



# Two-Part room temperature curing adhesive

## TECHNICAL DATA

PROPERTIES	DATA	UNIT	TEST METHOD
Composition	Ceramic powder filled curable gel	/	
Component style	Two-Part	/	
Color	A: White ; B: Purple	/	Visual
Viscosity	350,000	cps	ASTM D2196
The mixing ratio	1:1	/	
Operation time	2H (25°C)	Hour	Internal Lab
Curing Time	18H (25°C) 0.5H (120°C)	Hour	Internal Lab

### PRODUCT CHARACTERISTICS AFTER CURING

Density	2.92	g/cm <sup>3</sup>	ASTM D792
Hardness	50	Shore 00	ASTM D2240
Operating temperature	-40~150	°C	Internal Lab
Minimum interface thickness	0.1	mm	Internal Lab

### THERMAL PROPERTIES

Thermal conductivity	3.0	W/M·k	ASTM D 5470
----------------------	-----	-------	-------------

### ELETRICAL PROPERTIES

Volume resistivity	$\geq 1.0 \times 10^{13}$	Ohm-cm	ASTM D 257
Dielectric strength	$\geq 10$	KV/mm	ASTM D 149

### FLAME RETARDANT PROPERTIES

Flame retardant rating	V-0	/	UL94
------------------------	-----	---	------

#### ATTENTION

- Do not eat
- Keep out of the reach of children
- Keep the product away from fire
- Please confirm the correctness before using

#### HOW TO ORDER

- 25 cc\*2 200cc \*2 or 600cc \*2 Syringe packaging
- 5 gallon tank pack
- Fast or slow room temperature cure products can be ordered

#### STORAGE AND SHELF LIFE

- The product needs to be sealed and stored in an environment of 0-35°C and no more than 65% relative humidity.
- Storage Validity: 6 Months from shipping date.

Resived date:2023-11-06

Long Young Electronic Co.

Tel: 86.512.57668990

Fax: 86.512.57669500

